

Hysol

PC88

March 2013

PRODUCT DESCRIPTION

PC88 provides the following product characteristics:

Technology	Acrylic
Appearance	Clear liquid
Cure	Hot air drying
Product Benefits	<ul style="list-style-type: none"> • Toluene-free • Single component • Fluorescent under UV light • Superior toughness and abrasion resistance
Operating Temperature - Continuous	-40 to 125°C
Application	Conformal coating
Dried Film Thickness	25 to 100µm
Typical Assembly Applications	Printed circuit board coating

PC88 is a one component solvent based Acrylic conformal coating, designed to provide environmental and mechanical protection to printed circuit boards.

Components and joints may be repaired by heating the coating with a soldering iron for easy removal, or the entire coating may be removed with a suitable solvent. When fully dried, the material has superior toughness and abrasion resistance. Even after long environmental exposure, the coating retains its very light color. PC88 one component conformal coating is designed to provide environmental and mechanical protection to printed circuit boards used in automotive, military and other electronic applications.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content, %	24
Specific Gravity @ 25°C	0.902
Viscosity, Brookfield - LV, 25 °C, mPa·s (cP):	
Spindle 1, speed 30 rpm	65
Shelf Life @ 25°C, days	183
Flash Point ISO 13736:1997, BS 2000 Part 170:1995, Abel Cup, °C	7.75

TYPICAL DRYING PERFORMANCE

Recommended Drying Conditions

45 minutes @ 75 °C

Alternative Drying Conditions

24 hours @ 25 °C

Tack Free Time

For a 120µm wet film, @ 25°C / 35% RH, on glass plate, <10 minutes

Drying of the coating is contingent on solvent evaporation. Drying at temperatures higher than that recommended could cause formulation of bubbles if bulk solvent is not allowed to evaporate before oven placement.

Optimization of the drying schedule is possible to reduce the time listed above. Drying times will depend on film thickness and circuit board design.

For optimum performance, boards should be air dried at least 30 minutes @ 25°C to remove solvents before final oven drying (or before applying additional coats).

Deaeration is not suggested.

The above cure profile is a guideline recommendation. Cure rate and ultimate depth of cure depend on light intensity, spectral distribution of light source, exposure time and the light transmittance of the substrate.

TYPICAL PROPERTIES OF CURED MATERIAL

Electrical Properties

Insulation Resistance , 25 to 75 µm film:		
Initial	25°C/50% R.H.	2.8×10 ¹²
Cycle 4	65°C/95% R.H.	9.7×10 ¹⁰
Cycle 7	65°C/95% R.H.	9.9×10 ¹⁰
Cycle 10	65°C/95% R.H.	1.2×10 ¹¹
24hours after Cycle 10	25°C/50% R.H.	2.7×10 ¹²
Dielectric Strength , ASTM D149, volts/mil		1,500
Dielectric Constant / Dissipation Factor:		
@ 100Hz:		
@ 25°C		2.56/0.067
@ 60°C		2.87/0.045
@ 90°C		3.01/0.011
@ 110°C		3.21/0.033
@ 10kHz:		
@ 25°C		2.41/0.033
@ 60°C		2.56/0.056
@ 90°C		2.89/0.034
@ 110°C		3.02/0.024
@ 100kHz:		
@ 25°C		2.19/0.018
@ 60°C		2.45/0.063
@ 90°C		2.76/0.056
@ 100°C		2.89/0.016

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).



Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

DIRECTIONS FOR USE

1. Any tank should be pressurized with dry nitrogen..
2. Ideally applied via non-atomised selective film coater.
3. Do not use hand gun spray tool as this will lead to clogging of the nozzle.
4. Substrate cleanliness is paramount in promoting adhesion and preventing underfilm corrosion of copper conductors.
5. Furthermore compatibility with solder paste and flux etc should always be verified.
6. Removal of liquid or dried PC88 can be achieved with Xylene or a Ketone (e.g. MEK).

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 25°C. Storage below 5°C or above 30°C can adversely affect product properties.

Once opened, containers should be purged with dry nitrogen.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference **N/A**